



(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
16.07.2003 Bulletin 2003/29

(51) Int Cl.7: **F02F 7/00, F02F 1/16**

(21) Application number: **97117840.5**

(22) Date of filing: **15.10.1997**

(54) **An internal combustion engine cylinder block and manufacturing method**

Brennkraftmaschine-Zylinderblock und dessen Verfahren

Bloc-cylindres pour un moteur à combustion interne et méthode de sa fabrication

(84) Designated Contracting States:
DE FR GB

(30) Priority: **16.10.1996 JP 27364596**

(43) Date of publication of application:
22.04.1998 Bulletin 1998/17

(73) Proprietor: **TOYOTA JIDOSHA KABUSHIKI**
KAISHA
Aichi-ken (JP)

(72) Inventors:
• **Takami, Toshihiro**
Toyota-shi, Aichi-ken (JP)

- **Karakl, Mitsuhiro**
Toyota-shi, Aichi-ken (JP)
- **Kenmochi, Masamitu**
Toyota-shi, Aichi-ken (JP)
- **Sasada, Koichiro**
Toyota-shi, Aichi-ken (JP)

(74) Representative: **Kügele, Bernhard et al**
Novagraaf SA
25, Avenue du Pailly
1220 Les Avanchets - Geneva (CH)

(56) References cited:
EP-A- 0 554 575 **US-A- 1 721 197**
US-A- 4 005 991 **US-A- 4 469 060**
US-A- 5 562 073

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description**BACKGROUND OF THE INVENTION****1. Field of the Invention**

[0001] The present invention relates to a cylinder block of an internal combustion engine and, more particularly, to a semi-wet liner type cylinder block in which a cylinder liner is integrally cast and a method for manufacturing such a cylinder liner.

2. Description of the Related Art

[0002] Conventionally, a wet liner type cylinder block is a known type of cylinder block for an internal combustion engine. In the wet liner type cylinder block, the cylinder liner is cooled directly by coolant in a water jacket by locating the cylinder liner so that at least a part of the cylinder liner is exposed to the water jacket. Such a wet liner type cylinder block can be manufactured by integrally casting a cylinder liner in a cylinder block body as disclosed in Japanese Laid-Open Patent Application No.5-177334.

[0003] Generally, a cylinder block body is made of an aluminum alloy in order to reduce its weight, whereas a cylinder liner is made of cast iron to provide an anti-abrasion characteristic. Since aluminum alloy has a thermal expansion coefficient greater than that of cast iron, the cylinder block body expands more than the cylinder liner when a temperature of the cylinder liner is increased due to operation of the internal combustion engine. As mentioned above, the conventional cylinder block is manufactured by integrally casting the cylinder liner in the cylinder block. Thus, when the cylinder block body expands further than the cylinder liner, it is possible that a gap is formed between the cylinder block body and the cylinder liner. Since an outer surface of the cylinder liner is exposed to the water jacket, an interface between the cylinder block body and the cylinder liner is exposed to the water jacket. Accordingly, if a gap is formed between the cylinder block body and the cylinder liner, it is possible that a coolant can intrude into the crank case via the gap.

[0004] Reference is made to EP-A-0554575 relative to which the invention is characterised. Reference is also made to US 1721197 and US 5562073.

SUMMARY OF THE INVENTION

[0005] It would be desirable to provide an improved and useful cylinder block of an internal combustion engine and a manufacturing method therefor in which the above-mentioned problems are eliminated.

[0006] It would also be desirable to provide a cylinder block and a manufacturing method therefor in which a portion between the cylinder block body and the cylinder liner is sealed against coolant entry, and thereby the

coolant is prevented from intruding into the crank case.

[0007] In a first aspect, the invention provides a cylinder block of an internal combustion engine, comprising:

a cylinder block body made of a first material; and
a cylinder liner cast in said cylinder block body, said cylinder liner made of a second material different from said first material,

wherein said cylinder liner comprises an engaging portion shaped to interfit with a mating portion of said cylinder block body

characterised by said engaging portion of said cylinder liner being outside said mating portion in a radial direction of said cylinder liner so as to prevent separation of said cylinder liner and said cylinder block body in a radial direction of said cylinder liner, when said cylinder block body expands in use.

[0008] Accordingly, when the cylinder block body expands further than the cylinder liner, the portion of the cylinder block body tightly contacts the engaging portion of the cylinder liner. Thereby, a seal against the coolant is provided at an interface between the cylinder block body and the cylinder liner.

[0009] In one embodiment according to the present invention, the engaging portion may comprise a protrusion protruding outwardly from an outer surface of the cylinder liner in a radial direction, the protrusion having an end portion extending in a direction of a longitudinal axis of the cylinder liner.

[0010] According to this embodiment, the end portion of the protrusion engages the portion of the cylinder block body from outside of the portion of the cylinder block body in a radial direction. Thereby, a seal against the coolant is positively provided at an interface between the portion of the cylinder block body and the end of the protrusion protruding from the cylinder liner.

[0011] Additionally, the engaging portion may comprise a hollow space formed in the cylinder liner, the hollow space having an opening in an outer surface of the cylinder liner, an area of the hollow space being greater than an area of the opening when viewed in a radial direction of the cylinder liner.

[0012] In one embodiment according to the present invention, the engaging portion may include a first protrusion and a second protrusion adjacent to the first protrusion, the first and second protrusions protruding outwardly from an outer surface of the cylinder liner, each of the first and second protrusions having an end portion extending in opposite directions toward each other in a direction of a longitudinal axis of the cylinder liner.

[0013] According to this embodiment, a seal can be provided between the portion of the cylinder block body protruding through a portion between the first and second protrusions.

[0014] Additionally, each of the first and second protrusion has an undercut portion in an area connecting

to the outer surface of the cylinder liner when viewed from outside in a radial direction of the cylinder liner.

[0015] According to this embodiment, the cylinder liner engages the cylinder block body from outside in a radial direction in the undercut portion as well as the end portions of the first and second protrusions. Thus the number of sealing portions is increased, resulting in a positive seal against the coolant.

[0016] In one embodiment according to the present invention, an uneven portion is provided to the outer surface of the cylinder liner between the first and second protrusions along a circumferential direction of the cylinder liner.

[0017] Accordingly, a relative displacement between the cylinder liner and the cylinder block body in the circumferential direction is prevented by the unevenness. When expansion occurs in the cylinder block body that is greater than the expansion in the cylinder liner, a relative displacement occurs in the interface between the cylinder liner and the cylinder block body in the circumferential direction as well as in a radial direction. Accordingly, if the relative displacement in a radial direction is restricted, the relative displacement in the circumferential direction can be restricted. Thereby, formation of a gap in an interface between the cylinder block and the cylinder liner is prevented, resulting in an improved sealing effect against entry of the coolant at the interface.

[0018] In one embodiment according to the present invention, the engaging portion may include a first protrusion and a second protrusion adjacent to the first protrusion, the first and second protrusions protruding outwardly from an outer surface of the cylinder liner, the first and second protrusions slanting toward each other.

[0019] Additionally, in one embodiment according to the present invention, the engaging portion may include a circumferentially extending portion connected to an outer surface of the cylinder liner, the circumferentially extending portion being positioned a predetermined distance away from the outer surface of the cylinder liner in a radial direction of the cylinder liner, the circumferentially extending portion having a plurality of openings connecting outside and inside of the circumferentially extending portion.

[0020] Accordingly, the circumferentially extending portion engages a portion of the cylinder block body located inside the circumferentially extending portion from outside in a radial direction. Thus, a positive sealing effect is provided between the circumferentially extending portion and the portion of the cylinder block body.

[0021] Additionally, the predetermined distance may be greater than a width of a portion of the cylinder block body positioned on the outside of the circumferentially extending portion, the width being measured in a radial direction of the cylinder liner.

[0022] When the cylinder liner is cast, the molten metal is introduced into a space between the circumferentially extending portion and an outer surface of the cylinder liner through the openings formed in the circum-

ferentially extending portion. In a cooling process after the molten metal is filled, a flow of the molten metal occurs in a direction from outside the circumferentially extending portion to the space between the circumferentially extending portion via the openings due to the shrinkage of the molten metal in a radially inward direction. Thus, a good sealing effect is obtained in an area adjacent to the openings.

[0023] In one embodiment according to the present invention, the circumferentially extending portion may be connected to the cylinder at opposite sides thereof.

[0024] Alternatively, the circumferentially extending portion may be connected to the cylinder liner by a single rib at a middle position between opposite sides of the circumferentially extending portion.

[0025] Additionally, the circumferentially extending portion may be connected to the cylinder liner by a plurality of ribs each of which extends in a direction parallel to a longitudinal axis of the cylinder liner.

[0026] Further, in the cylinder block according to the present invention an uneven portion may be provided on an outer surface of the cylinder liner in a portion contacting the cylinder block body in a circumferential direction. In a further aspect, the invention provides a method for manufacturing a cylinder block of an internal combustion engine, comprising:

a cylinder block body made of a first material; and a cylinder liner cast in said cylinder block body, said cylinder liner made of a second material different from said first material, said cylinder liner having an engaging portion shaped to interfit with a mating portion of said cylinder block body, said engaging portion of said cylinder liner being outside said mating portion in a radial direction of said cylinder liner so as to prevent separation of said cylinder liner and said cylinder block body in a radial direction of said cylinder liner, when said cylinder block body expands in use, said method characterised by:

a first step of placing a core in a predetermined position inside a mold, said core having an inner surface for forming said engaging portion; a second step of die matching a liner pattern with respect to said core, said liner pattern having a contour substantially the same as said cylinder liner other than a portion corresponding to said engaging portion, said liner pattern comprising a combination of a plurality of pieces so that said liner pattern is die matched by positioning each of said pieces in a predetermined position inside said core; a third step of forming an outer surface forming mold corresponding to an outer surface of said cylinder liner by filling a mold material in a cavity formed between said mold and each of said core and said liner pattern and solidifying the

mold material in said cavity so as to unitize the mold material and said core;

a fourth step of removing said liner pattern from said mold;

a fifth step of placing an inner surface die in a predetermined position inside said outer surface forming mold, said inner surface die having a contour substantially the same as a contour of an inner surface of said cylinder liner; a sixth step of forming a liner forming mold by filling a mold material in said inner surface die so as to form an inner surface mold having a contour substantially the same as the contour of the inner surface of said cylinder liner and solidifying the mold material in said inner surface die so as to unitise said outer surface forming mold and said inner surface forming mold; and

a seventh step of casting said cylinder liner by filling molten metal in a cavity formed by said outer surface forming mold and said inner surface forming mold of said liner forming mold; and

an eight step of insertion casting said cylinder block with said cylinder liner inserted in said cylinder block.

[0027] In this method, the liner pattern is divided into a plurality of pieces. Thus, die matching of the liner pattern inside the core can be achieved by arranging each piece of the liner pattern in a predetermined position inside the core. Then, in the third step, the mold forming the engaging portion of the cylinder liner is formed by the inner surface of the core. Additionally, the mold which forms the outer surface of the cylinder liner other than the engaging portion is formed by the mold material filled around the liner pattern. These molds are utilised so that the mold for forming the outer surface of the cylinder liner is formed. By using the outer surface forming mold, the cylinder liner having the engaging portion can be formed which engaging portion engages the cylinder block body from outside in a radial direction.

Other features and advantages of the present invention will become more apparent from the following detailed description when read in conjunction with the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

[0028]

FIG.1 is a plan view of a cylinder block according to a first embodiment of the present invention;

FIG.2 is a cross-sectional view taken along a line II-II of FIG.1;

FIG.3 is a cross-sectional view taken along a line III-III of FIG.2;

FIG.4 is an enlarged cross-sectional view of an en-

gaging portion provided to a cylinder liner of the first embodiment;

FIG.5 is an enlarged cross-sectional view of an engaging portion provided to a cylinder liner of a second embodiment of the present invention;

FIG.6 is an enlarged cross-sectional view of an engaging portion provided to a cylinder liner of a third embodiment of the present invention;

FIG.7 is an enlarged cross-sectional view of an engaging portion provided to a cylinder liner of a fourth embodiment of the present invention;

FIG.8 is an enlarged cross-sectional view of an engaging portion provided to a cylinder liner of a fifth embodiment of the present invention;

FIG.9 is a cross-sectional view taken along a line IX-IX of FIG.8;

FIG.10 is a view of an engaging portion provided to a cylinder liner according to a sixth embodiment, viewed from outside in a radial direction;

FIG.11 is a cross-sectional view taken along a line XI-XI of FIG.10;

FIG.12 is an enlarged cross-sectional view of an engaging portion provided to a cylinder liner of a seventh embodiment of the present invention;

FIG.13 is an perspective view of an engaging portion provided to a cylinder liner of an eighth embodiment of the present invention;

FIG.14 is a plan view of a core used for manufacturing a cylinder block according to the first embodiment of the present invention;

FIG.15 is a cross-sectional view of the core;

FIG.16 is a cross-sectional view for explaining a manufacturing method of the core;

FIG.17 is a plane view of a mold for manufacturing the cylinder block according to the first embodiment of the present invention in a state where the core is placed in a predetermined position;

FIG.18 is a cross-sectional view taken along a line XVIII-XVIII of FIG.17;

FIG.19 is a front view of a liner pattern;

FIG.20 is a plan view of the liner pattern;

FIG.21 is a plan view of the liner pattern which is divided into pieces;

FIG.22 is a front view of the liner pattern which is divided into pieces;

FIG.23 is a view of the liner pattern located in the mold for explaining die matching of the liner pattern inside the core;

FIG.24 is a view of the liner pattern located in the mold for explaining die matching of the liner pattern inside the core;

FIG.25 is a view of the liner pattern located in the mold in a state where the liner pattern is die matched in a predetermined position inside the core;

FIG.26 is an enlarged cross-sectional view of an engaging portion between an inner surface of the core and the liner pattern;

FIG.27 is a view for explaining a procedure for die matching an upper mold and a lower mold;

FIG.28 is a view of the upper mold and the lower mold which are die matched in predetermined positions;

FIG.29 is a view of the mold in a state where the liner pattern is removed after an outer mold pattern was formed;

FIG.30 is a cross-sectional view for explaining a procedure of die matching a bore die and an inner die;

FIG.31 is a cross-sectional view of the bore die and the inner die which are die matched;

FIG.32 is a cross-sectional view of the liner mold pattern after it is molded;

FIG.33 is a view for explaining a procedure of die matching the liner mold pattern in a mold;

FIG.34 is a cross-sectional view of the liner pattern die matched in the mold;

FIG.35 is a cross-sectional view of an engaging portion between the core and the liner pattern for manufacturing the cylinder liner according to the second embodiment of the present invention;

FIG.36 is a cross-sectional view of an engaging portion between the core and the liner pattern for manufacturing the cylinder liner according to the third embodiment of the present invention;

FIG.37 is a cross-sectional view of an engaging portion between the core and the liner pattern for manufacturing the cylinder liner according to the fifth embodiment of the present invention;

FIG.38 is a plan view of a part of the core for manufacturing the cylinder liner according to the fifth embodiment of the present invention;

FIG.39 is a cross-sectional view of an engaging portion between the core and the liner pattern for manufacturing the cylinder liner according to the seventh embodiment of the present invention; and

FIG.40 is a cross-sectional view of a part of a liner mold pattern for explaining a method for forming openings in an engaging portion of the cylinder liner according to the seventh embodiment.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0029] A description will now be given, with reference to FIGS.1 to 4, of a double cylinder type cylinder block 10 according to a first embodiment of the present invention. It should be noted that the present invention can be applied to a single cylinder type cylinder block or a multiple cylinder type cylinder block having a plurality of cylinders. FIG.1 is a plane view of a part of the cylinder block 10. FIGS.2 and 3 are cross-sectional views of the cylinder block 10 taken along a line II and a line III of FIG.1, respectively.

[0030] As shown in FIGS.1-3, the cylinder block 10 is constructed by casting cylinder liners 14 which are

made of cast iron into a cylinder block body 12 which is made of aluminum alloy. The cylinder block body 12 has two cylinders 16. The cylinder liners 14 are provided on an inner side of a corresponding cylinder 16. The cylinder liner 14 provides, on an inner side thereof, a cylinder bore 18 in which a piston (not shown in the figures) is movable therein, and provides a part of an inner wall of a water jacket 20 on an outer side thereof. Bolt holes 22 are provided around the water jacket 20 for mounting a cylinder head (not shown in the figures). The above-mentioned cylinder 16, water jacket 20 and bolt holes 22 are open in a deck surface 24 of the cylinder block body 12.

[0031] As shown in FIG.2, a plurality of ribs 14a are provided on a portion of an outer surface of the cylinder liner 14 which faces the water jacket 20. Since the ribs 14a are provided, a contact area between the cylinder liner and the coolant is increased, and thereby a cooling effect of the coolant is increased. A crank case 25 is provided in a portion under the cylinder 16 of the cylinder block 10 in FIG.2. Additionally, an engaging portion 26 is provided around the entire circumference of a portion of the cylinder liner 14, the engaging portion being cast within the cylinder block body 12. The structure of the engaging portion 26 will be described later.

[0032] As shown in FIG.3, the cylinder liner 14 has inter-bore water passages 14c, 14d and 14e which pass through a boundary portion between the adjacent cylinder bores in left and right directions in the figure. Since the inter-bore water passages 14c-14e are provided, a cooling effect is provided even in the boundary portion between the adjacent cylinder bores.

[0033] It should be noted that the cylinder block 10 is cast by pouring molten metal into a cavity formed between the cylinder liner 14 and a mold in a state where the cylinder liner 14 is placed in the mold with a core for forming the water jacket around the cylinder liner 14.

[0034] When the internal combustion engine is operated, a temperature of the cylinder block is increased. As mentioned above, the cylinder block body 12 is made of aluminum alloy, whereas the cylinder liner is made of cast iron. Since the thermal expansion coefficient of aluminum alloy is greater than the thermal expansion coefficient of cast iron, the cylinder block body 12 expands further than the cylinder liner 14. Accordingly, it is possible that a gap is formed between the cylinder block body 12 and the cylinder liner 14. Since the cylinder liner 14 constitutes a part of the inner wall of the water jacket 20 as mentioned above, the interface between the cylinder liner 14 and the cylinder block body 12 is exposed to the water jacket 20. Additionally, as shown in FIG.2, a lower end of the interface between the cylinder liner 14 and the cylinder block body 12 is exposed to the crank case 25. Thus, if a gap is formed between the cylinder liner 14 and the cylinder block body 12, it is possible that a coolant in the water jacket 20 could enter the crank case 25 through the gap.

[0035] On the other hand, in the cylinder block 10 ac-

cording to the present embodiment, since the cylinder liner 14 is provided with the engaging portion 26, an improved sealing effect is provided for a portion between the cylinder liner 14 and the cylinder block body 12 against entry of the coolant. Thus the coolant is prevented from entering into the crank case 25. A description will be given of the engaging portion 26a below.

[0036] FIG.4 is an enlarged cross-sectional view of the engaging portion 26 provided to the cylinder liner 14 according to the present embodiment, the engaging portion being cut in an axial direction of the cylinder liner 14. As shown in FIG.4, the engaging portion 26 includes a pair of protrusions 140 and 142 which protrudes in a radially outward direction from an outer surface of the cylinder liner 14. The protrusions 140 and 142 have bent portions 140a and 142a at their ends, respectively, which are bent so that the bent portions 140a and 142a are opposite each other in the axial direction of the cylinder liner 14. As mentioned above, the cylinder block 10 is cast by pouring molten metal into the cavity formed around the cylinder liner 14. Accordingly, the molten metal is filled in a space between the protrusions 140 and 142 of the engaging portion 26 of the cylinder liner 14, and an engaging protrusion 120 is formed on a surface of the cylinder block body 12 by the molten metal filled in the space between the protrusions 140 and 142. The engaging protrusion 120 has a top surface 120a and engaging surfaces 120b and 120c. The top surface 120a contacts a portion of the outer surface of the cylinder liner 14 between the protrusions 140 and 142. The engaging surfaces 120b and 120c engages the engaging surfaces 140b and 142b which are inner surfaces of the bent portions 140a and 142a.

[0037] According to the structure of the engaging portion 26, when a temperature of the cylinder block 10 is raised in association with an operation of the internal combustion engine, the outer diameter of the engaging surfaces 120b and 120c of the engaging protrusion 120 becomes greater than the inner diameter of the engaging surfaces 140b and 142b of the protrusions 140 and 142 since the cylinder block body 12 expands further than the cylinder liner 14. Accordingly, the engaging surfaces 120b and 120c and the engaging surfaces 140b and 142b press against each other and, thus, a sealing effect between the engaging surfaces 120b and 120c and the engaging surfaces 140b and 142b is improved. Thus, if the coolant from the water jacket 20 enters the interface between the cylinder block body 12 and the cylinder liner 14, the coolant is prevented from entering the crank case 25 since a tight seal is provided between the engaging surfaces 120b and 120c and the engaging surfaces 140b and 142b.

[0038] As mentioned above, in the present embodiment, the engaging protrusion 120 of the cylinder block body 12 engages the engaging portion 26 of the cylinder liner 14 so that the engaging protrusion 120 is positioned on the inner side of the engaging portion 26. Accordingly, when thermal expansion occurs in the cylinder block,

a seal against the coolant is provided by the engaging portion 26. Thus, the coolant is prevented from intruding into the crank case 25.

[0039] It should be noted that, as shown in FIG.2, in the cylinder block 10, the coolant 25 being prevented from entering the crank case 25 is ensured by providing the engaging portion 26 at two locations.

[0040] A description will now be given, with reference to FIGS.5 to 13, of other embodiments of the present invention. It should be noted that those embodiments features a structure of an engaging portion provided on an outer surface of a cylinder liner, and parts other than the engaging portion have the same structure as that of the above-mentioned first embodiment.

[0041] FIG.5 is an enlarged cross-sectional view of an engaging portion 28 formed on a cylinder liner 28 according to a second embodiment of the present invention, the engaging portion being cut in an axial direction of the cylinder liner 28. As shown in FIG.5, the engaging portion 30 of the present embodiment includes a pair of protrusions 32 and 34 which protrudes radially outwardly from an outer surface of the cylinder liner 28. The protrusions 32 and 34 are formed in an arc-like shape so that the cross sections of the protrusions 32 and 34 are convex shapes extending in opposite directions to each other along the axis of the cylinder liner 28.

[0042] According to the structure of the engaging portion 30, similar to the engaging portion 26 of the first embodiment, a seal against the coolant is achieved by the cylinder liner 28 being engaged with the cylinder block body 12 from an outer side in a radial direction at inner surfaces 32a and 34a of ends of the protrusions 32 and 34 and outer surfaces 32b and 34b near the roots of the protrusions 32 and 34. In this case, a sealing effect at an interface between the cylinder block 12 and the cylinder liner 28 is improved by sealing engagement at two portions for each of the protrusions 32 and 34 when thermal expansion occurs in the cylinder block 10.

[0043] FIG.6 is an enlarged cross-sectional view of an engaging portion 46 formed on a cylinder liner 44 according to a third embodiment of the present invention, the engaging portion being cut in an axial direction of the cylinder liner 44. As shown in FIG.6, the engaging portion 46 of the present embodiment includes a pair of protrusions 48 and 50 which protrudes radially outwardly from an outer surface of the cylinder liner 44. The protrusions 48 and 50 extend toward each other so that each of the protrusions provide a conical shape. According to the structure of the engaging portion 46, similar to the engaging portion 26 of the first embodiment, a seal effect against the coolant is achieved by the cylinder liner 44 being engaged with the cylinder block body 12 from an outer side in a radial direction at inner surfaces 48a and 50a of the protrusions 48 and 50.

[0044] It should be noted that as appreciated from the second and third embodiment, a sealing effect can be obtained even when a direction of engagement is inclined from a radial direction as long as a portion of the

cylinder block body is present on an inner side of a portion of the cylinder liner.

[0045] FIG.7 is an enlarged cross-sectional view of an engaging portion 40 formed on a cylinder liner 38 according to a fourth embodiment of the present invention. The engaging portion 40 of the present embodiment comprises a single protrusion 42 which has a construction similar to the protrusion 142 of the engaging portion 26 according to the above-mentioned first embodiment. In this structure, a sealing effect for an interface between the cylinder liner 38 and the cylinder block 12 against the coolant can be obtained when thermal expansion occurs in the cylinder block 10 since an inner surface 42b of a bent portion 42a engages the cylinder block body in a radial direction from the outer side. It should be noted that the protrusion 42 may have a structure similar to the protrusions 32 and 34 of the engaging portion 30 shown in FIG.5 or the protrusions 48 and 50 of the engaging portion 46 shown in FIG.6.

[0046] FIG.8 is an enlarged cross-sectional view of an engaging portion 54 formed on a cylinder liner 52 according to a fifth embodiment of the present invention, the engaging portion being cut in an axial direction of the cylinder liner 52. FIG.9 is a cross-sectional view taken along a line IX of FIG.8. As shown in FIG.8, the engaging portion 54 of the present embodiment includes protrusions 56 and 58 which have a structure similar to the protrusions 140 and 142 shown in FIG.4. In the present embodiment, similar to the first embodiment, a sealing effect can be obtained against entry of the coolant by inner surfaces of bent portions 56a and 58a provided on end portions of the protrusions 56 and 58. Additionally, as shown in FIG.9, the engaging portion 54 according to the present embodiment includes an uneven portion 60 formed on an outer surface of the cylinder liner 52 between the protrusions 56 and 58, the uneven portion 60 extending in a circumferential direction of the cylinder liner 52.

[0047] As mentioned above, when the temperature of the cylinder block 10 is raised, a gap is formed between the cylinder liner 52 and the cylinder block body 12 since the cylinder block body 12 expands more than the cylinder liner 52 due to a difference in the thermal expansion coefficient of the cylinder liner 52 and the cylinder block body 12. In such a case, in the interface between the cylinder liner 52 and the cylinder block body 12, a relative displacement in a circumferential direction occurs as well as a relative displacement in a radial direction. Accordingly, if the relative displacement between the cylinder block body 12 and the cylinder liner 52 in the circumferential direction is prevented, the relative displacement in the radial direction can be prevented.

[0048] In the present embodiment, the cylinder liner 52 and the cylinder block body 12 engages each other in the circumferential direction by the uneven portion 60. Accordingly, the relative displacement between the cylinder liner 52 and the cylinder block body 12 in the circumferential direction is restricted, and thereby the rel-

ative displacement between the cylinder liner 52 and the cylinder block body 12 in the radial direction is also restricted. Thus, formation of a gap between the cylinder liner 52 and the cylinder block body 12 is prevented.

[0049] As mentioned above, according to the engaging portion 54 of the present embodiment, when a thermal expansion occurs in the cylinder block 10, a sealing effect against entry of the coolant is improved by a synergistic effect of the bent portions 56a and 58a of the protrusions 56 and 58 and the uneven portion 60. Thereby, the coolant is more positively prevented from entering the crank case.

[0050] It should be noted that, in the present embodiment, although the uneven portion 60 is provided between the protrusions 56 and 58, the present invention is not limited to this structure, that is, the uneven portion 60 may be provided by a portion of the outer surface of the cylinder liner 52 which portion is cast within the cylinder block body 12. That is, the uneven portion 60 may be provided a portion in which the cylinder liner 52 contacts the cylinder block body 12.

[0051] A description will now be given, with reference to FIGS.10 and 11, of a sixth embodiment of the present invention. The sixth embodiment features an improvement of sealing characteristics against the coolant by increasing adhesion at a joining part between a cylinder liner 68 and the cylinder block body 12.

[0052] FIG.10 is a view of an engaging portion 70 formed on the cylinder liner 68 viewed from a outside in a radial direction of the cylinder liner 68. FIG.11 is a cross-sectional view taken along a line XI of FIG.10. As shown in FIGS.10 and 11, the engaging portion 70 includes an annular anchor portion 72 which is spaced apart from an outer surface of the cylinder liner 68 at a predetermined distance L in a radial direction of the cylinder liner 68. The anchor portion 72 is connected to the cylinder liner 68 by a rim portions 74 and 76 over the entire circumference of the cylinder liner 68 at its opposite ends in the axial direction of the cylinder liner 68. Accordingly, an annular space 78 having a thickness L in a radial direction is formed around the cylinder liner 68 by the anchor portion 72, the rim portions 74 and 76 and the outer surface of the cylinder liner 68. As shown in FIG.10, a plurality of openings 80 are provided at equal intervals in a circumferential direction. It should be noted that the distance L, that is, the thickness L of the annular space 78 is set to a value greater than a thickness M of a portion 12b of the cylinder block body 12 which is located around the anchor portion 72.

[0053] According to the structure of the anchor portion 70, when molten the cylinder block 10 is cast, the molten metal poured in a cavity fills the annular space 78 through the openings 80. In a process for cooling and solidification after the molten metal is poured, the molten metal shrinks so that a center plane of the thickness of the cylinder block body 12 moves radially inwardly and the thickness is reduced. In this case, as mentioned above, since the thickness L of the annular space 78 is

greater than the thickness M of the portion 12b of the cylinder block body 12, the center plane of the thickness in a portion constituted by the molten metal in the annular space 78, the opening 80 and the portion 12b of the cylinder block body 12 is shifted toward the annular space 78. Accordingly, in this portion, a flow is generated in the molten metal from the portion 12b of the cylinder block body 12 to the annular space 78. Due to the flow of the molten metal, adhesion between the anchor portion 72 and the cylinder block body 12 is improved in an area (a hatched area 72a in FIG.10) near the openings 80 of the anchor portion 72. Thus, in the present embodiment, a sealing effect against the coolant at the interface between the cylinder block body 12 and the cylinder liner 68 is improved by improving the adhesion between the anchor portion 72 and the portion 12b in the process for cooling and solidification. Thereby, the coolant is prevented from intruding into the crank case.

[0054] It should be noted that, in the present embodiment, similar to the first to fifth embodiments, a seal against the coolant at the interface between the cylinder liner 68 and the cylinder block body 12 is also provided by a inner surface of the anchor portion 72 being engaged with a portion of the cylinder block body 12 within the annular space 78 in a radial direction from an outer side.

[0055] A description will now be given, with reference to FIG.12, of a seventh embodiment of the present invention. FIG.12 is a cross-sectional view of an engaging portion 100 formed on a cylinder liner 98 according to the present embodiment. As shown in FIG.12, the engaging portion 100 comprises a rib 102 and an anchor portion 104. The rib 102 extends radially outwardly from an outer surface of the cylinder liner 98. The anchor portion 104 has an annular shape and is apart from the outer surface of the cylinder liner 98 by a distance H. The anchor portion 104 is provided with openings 108 and 110 formed at equal intervals in a circumferential direction. The distance H is set to a value greater than a thickness K of a portion 12c around the anchor portion 104 of the cylinder block body 12.

[0056] According to the above-mentioned structure, similar to the engaging portion 80 of the sixth embodiment, a flow of the molten metal is generated from an outer side to an inner side of the anchor portion 104 via the openings 108 and 110 in the process for cooling and solidification. Thus, adhesion between the anchor portion 104 and the portion 12c is improved at portions of the outer surface of the anchor portion 104 around the openings 108 and 110 and, thereby, a seal against the coolant can be provided.

[0057] It should be noted that, in the present embodiment, although the anchor portion 104 is supported by the rib 102 circumferentially extending on the cylinder liner 98, the anchor portion may be supported by a plurality of ribs 103 arranged at a predetermined interval in a circumferential direction, each of which extends in a radial direction of the cylinder liner 98 as shown in a per-

spective view of FIG.13.

[0058] It should be noted that, in the sixth and seventh embodiments, the anchor portions 72 and 104 corresponds to an engaging arrangement.

[0059] A description will now be given, with reference to FIGS.14 to 34, of an example of a manufacturing method for the cylinder block according to the first embodiment of the present invention. The manufacturing method features, especially, a formation of a configuration having a space located at an interior of the cylinder liner like the engaging portion 26 of the cylinder liner 14.

[0060] FIG.14 is a plan view of a core 200 for forming the engaging portion on the cylinder liner 14. FIG.15 is a cross-sectional view taken along a line XV-XV of FIG. 14. As shown in FIG.14, the core 200 is a sand mold corresponding to a double cylinder structure. As shown in FIG.15, the core 200 has a portion 200a formed on an inner circumferential surface thereof so as to form the engaging portion 26 of the cylinder liner 14. FIG.16 is a cross-sectional view for explaining a manufacturing method of the core 200. As shown in FIG.16, the core 200 can be manufactured by filling a molding material into a cavity 201c formed by a combination of a mold 201a and a mold 201b. It should be noted that the core 200 can be formed with a cross section having an arbitrary configuration by changing the shapes of the molds 201a and 201b.

[0061] The core 200 is placed inside a main mold 202. FIG.17 is a plan view of the main mold 202 in which the core 200 is placed. FIG.18 is a cross-sectional view taken along a line XVIII-XVIII of FIG.17. The main mold 202 is constituted by a combination of four molds 202a, 202b, 202c and 202d. A cavity 202e is formed inside the molds 202a, 202b, 202c and 202d when they are combined. Additionally, the main mold 202 is provided with protrusions 203a to 203f (only protrusions 203c and 203f are shown in the figure) arranged in two different levels. An end of each of the protrusions 203a to 203f engages an outer surface of the corresponding core 200. The cores 200 are held in predetermined positions by the protrusions 203a to 203f as shown in FIGS.17 and 18.

[0062] As shown in FIG.18, the main body 202 is placed on a top surface of a molding die 204. The molding die 204 has blow ports 204a and 204b which connects the cavity 202e to a bottom surface 204 of the molding die 204. Additionally, the molding die 204 has a liner pattern table 204c on which a liner pattern 206 (described later) is seated.

[0063] After the cores 200 are placed, the liner pattern 206 is positioned inside the cores 200. FIG.19 is a front view of the liner pattern 206. FIG.20 is a plan view of the liner pattern 206. The liner pattern 206 is a hollow metal mold having a closed top end and an open bottom end. As shown in FIGS.19 and 20, the liner pattern 206 has a plurality of water passage holes 206a to 206c so as to form the inter-bore water passages 14c to 14e (refer to FIG.3). The liner pattern 206 is divided in to the

outer pieces 208 and 210, middle pieces 212, 214, 216 and 218 and inter-bore pieces 220 and 222 by dividing lines 207a to 207m. FIGS.21 and 22 show a state where the liner 206 is divided into the pieces 208 to 222.

[0064] FIGS.23 to 25 are views for explaining a method for die matching the liner pattern 206 inside the core 200. When the liner pattern 206 is die matched with the core 200, the outer pieces 208 and 210 and the inter-bore pieces 220 and 222 are inserted into inside the cores 200 as shown in FIG.23. Thereafter, each piece is moved in directions as indicated by arrows in FIG.23 so as to die match each piece in a predetermined position with respect to the cores 200. Then, as shown in FIG.24, the middle pieces 212 to 218 are placed between the outer pieces 208 and 210 and the inter-bore pieces 220 and 222, respectively. Thereafter, the middle pieces 212 to 218 are moved in directions indicated by arrows in FIG.24. Thereby, the middle pieces 212 to 218 are die matched in predetermined positions as shown in FIG.25. It should be noted that the liner pattern table 204b of the molding die 204 is arranged so that the pieces 208 to 222 are placed in predetermined positions along the axial direction in a state where the pieces constituting the liner pattern 206 are placed on the liner pattern table 204b. Thereby, die matching of the liner pattern can be easily performed.

[0065] FIG.26 is a cross-sectional view of a portion where the core 200 engages the liner pattern 206, the portion being cut along the axial direction of the liner pattern 206. As shown in FIG.26, a pair of protrusions 206a and 206b are formed on an outer surface of the liner pattern 206, the protrusions engaging the portion 200a of the core 200. The position of the protrusions 206a and 206b correspond to the engaging portion 26 of the liner 14. The core 200 and the liner pattern 206 engage with each other so that the portion 200a of the core 200 is placed within a space defined by the protrusions 206a and 206b. According to this structure, when the mold material is filled around the liner pattern 206 and the mold material and the core 200 becomes a solid piece, the mold material does not enter the above-mentioned space. Thus, a portion of the sand mold which forms an outer surface of the engaging portion 26 is formed by an upper surface of the protrusion 206a and a lower surface of the protrusion 206b in FIG.26, and a portion of the sand mold which forms an inner surface of the engaging portion 26 is formed by the portion 200a of the core 200.

[0066] After the die matching of the liner pattern 206 is completed, an upper die 224 and a lower die 226 are die matched from the upper side and the lower side of the liner pattern 206 as shown in FIG.27. The lower die 226 is provided with two cylindrical portions 226a and 226b which are inserted inside the liner pattern 206 by passing through openings provided in the liner pattern table 204c of the liner pattern 204. Additionally, the upper die 224 is provided with table portions 224a and 224b which engage the top surface of the liner pattern

206. FIG.28 shows a state where the upper die 224 and the lower die 226 are die matched in predetermined positions. As shown in FIG.28, the liner pattern 206 is held in a predetermined position by the upper die 224 and the lower die 226 being die matched. In this state, a cavity 228 is formed between an inner surface of the main mold 202 and the outer surface of the liner pattern 206.

[0067] After the die matching of the upper die 224 and the lower die 226 is completed, the mold material is introduced into the cavity 228 through the blow ports 204a and 204b. Then, catalytic gas is passed through the mold material filled in the cavity 228 so as to solidify the mold material, and the solidified material and the cores 200 are formed into one piece. After the upper die 224 and the lower die 226 are removed, the middle pieces 212 to 218 are pulled out first, and then the outer pieces 208 and 210 and the inter-bore pieces 220 and 222 are gathered toward the center of the corresponding cylinder and pulled out as shown in FIG.29. In this state, an outer mold pattern 230 is formed in which the mold material filled in the cavity 228 and the cores 200 are combined into one piece. It should be noted that an engaging step 230a is formed on an inner surface of the outer mold pattern 230 by an upper peripheral corner of the liner pattern 206. Additionally, water passage forming portions 230a to 230c are formed by the mold material filled in the water passage holes 206a to 206c of the liner pattern 206.

[0068] After the outer mold pattern 230 is formed which forms the outer surface of the cylinder liner 14, another mold pattern is formed which forms the inner surface, that is, the cylinder bore of the cylinder liner 14. First, as shown in FIG.30, an inner die 234 and a bore die 236 are die matched from the upper side and the lower side of the outer mold pattern 230. FIG.32 shows a state where the inner die 234 and the bore die 236 are die matched. As shown in FIG.3 and 31, the inner die 234 is provided with cylindrical portions 234a and 234b which protrude into inside the outer mold pattern 230 when it is die matched. The bore die 236 is provided with inner mold patterns 236a and 236b having a configuration the same as that of each of the cylinder bore surfaces. The inner mold patterns 236a and 236b extend upwardly so that each of the inner mold patterns 236a and 236b faces an inner surface of the corresponding inner surface of the outer mold pattern 230 when the bore die 236 is die matched. An end of each of the inner mold patterns 236a and 236b engages the engaging step 230a when the bore die is die matched. Further, the bore die 236 is provided with blow ports 236c and 236d which connect a space formed under a bottom surface of the bore die 236 to spaces formed inside the inner mold patterns 236a and 236b.

[0069] A mold material is introduced into cavities 238 formed inside the inner mold patterns 236a and 236b of the bore die 236 through the blow ports 236c and 236d. In this case, upper ends of the inner mold patterns 236a and 236b of the bore die 236 engage the engaging step

230a of the outer mold pattern 230. Thereby, the mold material is prevented from entering a space formed between outer surfaces of the inner mold patterns 236a and 236b and the outer mold pattern 230. The mold material filled in the cavity 238 is solidified by a catalytic gas being passed therethrough. The solidified mold material is unitized with the outer mold pattern at a portion above the engaging step 230. Then, as shown in FIG. 32, the upper die 234 and the lower die (bore die) 236 are removed upwardly and downwardly, respectively, and the parts of the main mold 202 are moved in side directions. Thus, a liner mold pattern 242 is taken out in which the mold material filled in the cavity 238 and the outer mold pattern 230 are unitized. In the liner mold pattern 242, a liner forming cavity 242a is formed by a space occupied by the inner mold patterns 236a and 236b of the bore die 236 and a space between the inner mold patterns 236a and 236b and the outer mold pattern 230. Additionally, hollow portions 242b and 242c are formed which correspond to the cylindrical portions 242b and 242c, respectively. The hollow portions 242b and 242c are provided for discharging a gas included in the molten metal of the liner mold pattern 242.

[0070] After the liner mold pattern 242 is formed which is a pattern for forming the cylinder liner 14, a liner casting upper mold 244 and a liner casting lower mold 246 are die matched to the liner mold pattern 242 from the upper side and the lower side 242, respectively, as shown in FIG.33. FIG.34 shows a state in which the liner casting upper mold 244 and the liner casting lower mold 246 are die matched. As shown in FIG.34, the liner casting upper mold 244 is provided with a gate 244a. The liner casting lower mold 246 is constructed so that a runner 246a is formed when it is die matched, the runner 246 connecting the gate 244a to the liner forming portion 242a.

[0071] After the die matching of the liner casting upper mold 244 and the liner casting lower mold 246 is completed, the molten cast iron is introduced into the forming portion 242a of the liner mold pattern 242 from the gate 244a of the liner casting upper mold 244 so as to cast the cylinder liner 14.

[0072] Thereafter, a core is attached to an outer surface of the cylinder liner 14 so as to form the water jacket 20, and the casting molds are arranged around the cylinder liner 14. Then molten aluminum alloy is filled in a cavity formed between the casting molds and the cylinder liner 14 so as to cast the cylinder block 10.

[0073] As mentioned above, in the present embodiment, the core 200 for forming the engaging portion 26 is formed separately from the outer mold pattern 230 for forming the outer surface of the cylinder liner 14. Thereafter, the core 200 and the outer mold pattern 230 are unitized so as to form the cylinder liner having a space which expands inside the cylinder liner like the engaging portion 26.

[0074] It should be noted that, although in the present embodiment the cylinder liner 14 according to the first

embodiment is manufactured, the cylinder liners according to other embodiments can be manufactured by changing a contour of the cross-section of the core 200 and the liner pattern 206. For example, when the cylinder liner 28 shown in FIG.5 is manufactured, the outer surface configuration of the protrusions 206a and 206b of the liner pattern 206 is to be formed to correspond to the configuration of the protrusions 32 and 34 of the engaging portion 30 as shown in FIG.35. Additionally, when the cylinder liner 44 shown in FIG.6 is manufactured, the portion 200a of the core 200 and the protrusions 206a and 206b of the liner pattern 206 are to be formed as that shown in FIG.36.

[0075] Additionally, when the cylinder liner 68 shown in FIG.11 is manufactured, the portion 200a of the core 200 and the protrusions 206a and 206b of the liner pattern 206 are formed as shown in FIG.37. In this case, the core 200 is to be formed to have a plurality of connecting portions 200b periodically arranged in a circumferential direction as shown in a plane view of FIG.38.

[0076] Further, when the cylinder liner 68 shown in FIG.12 is manufactured, the core 200 and the liner pattern 206 are to be formed as that shown in FIG.39. Then, when the cylinder liner 98 is cast by the liner mold pattern 242, piercing rods 250 are inserted into the liner mold pattern 242 as shown in FIG.40.

[0077] The present invention is not limited to the specifically disclosed embodiments, and variations and modifications may be made without departing from the scope of the present invention, as defined in the appended claims.

Claims

1. A cylinder block of an internal combustion engine, comprising:
 - a cylinder block body made of a first material; and
 - a cylinder liner (14; 28; 44; 38; 52; 68; 98) cast in said cylinder block body, said cylinder liner made of a second material different from said first material,
 wherein said cylinder liner comprises an engaging portion (26; 30; 40; 46; 54; 70; 100) shaped to interfit with a mating portion of said cylinder block body
 - characterised by said engaging portion of said cylinder liner being outside said mating portion in a radial direction of said cylinder liner so as to prevent separation of said cylinder liner and said cylinder block body in a radial direction of said cylinder liner, when said cylinder block body expands in use.
2. The cylinder block as claimed in claim 1, wherein said engaging portion of said cylinder liner is formed

along an entire circumference on an outer surface of said cylinder liner which is casted in said cylinder block body.

3. The cylinder block as claimed in claim 1 or 2, **characterized in that** said engaging portion (26; 30; 40; 46; 54) comprises a protrusion (140, 142; 32, 34; 48; 50; 42; 56; 58) protruding outwardly from an outer surface of said cylinder liner (14; 28; 44; 38; 52) in a radial direction, said protrusion having an end extending in a direction of a longitudinal axis of said cylinder liner.
4. The cylinder block as claimed in claim 1, **characterized in that** said engaging portion comprises a hollow space formed in said cylinder liner (14; 28; 44; 56), said hollow space having an opening in an outer surface of said cylinder liner, an area of said hollow space being greater than an area of said opening when viewed in a radial direction of said cylinder liner.
5. The cylinder block as claimed in claim 3, **characterized in that** said engaging portion includes a first protrusion (140; 32; 48; 56) and a second protrusion (142; 34; 50; 58) adjacent to said first protrusion, said first and second protrusions protruding outwardly from an outer surface of said cylinder liner (14; 28; 44; 52), each of said first and second protrusions having an end portion extending in directions toward each other in a direction of a longitudinal axis of said cylinder liner.
6. The cylinder block as claimed in claim 3 or 5, **characterized in that** each of said first and second protrusion (32, 34) has an undercut portion (32b, 34b) in an area connecting to the outer surface of said cylinder liner when viewed from outside in a radial direction of said cylinder liner.
7. The cylinder block as claimed in claim 3 or 5 **characterized in that** an uneven portion (60) is provided to the outer surface of said cylinder liner (52) between said first and second protrusions (56, 58) along a circumferential direction of said cylinder liner.
8. The cylinder block as claimed in claim 3, **characterized in that** said engaging portion (46) includes a first protrusion (48) and a second protrusion (50) adjacent to said first protrusion, said first and second protrusions protruding outwardly from an outer surface of said cylinder liner (44), said first and second protrusions slanting toward each other.
9. The cylinder block as claimed in claim 1 or 2, **characterized in that** said engaging portion (70; 100) includes a circumferentially extending portion (72;

104) connected to an outer surface of said cylinder liner (68; 98), said circumferentially extending portion being positioned a predetermined distance (L; H) away from said outer surface of said cylinder liner in a radial direction of said cylinder liner, said circumferentially extending portion having a plurality of openings (80; 108, 110) connecting outside and inside of said circumferentially extending portion.

10. The cylinder block as claimed in claim 9, **characterized in that** said predetermined distance (L; H) is greater than a width (M; K) of a portion (12b; 12c) of said cylinder block body positioned on the outside of said circumferentially extending portion, said width being measured in a radial direction of said cylinder liner.
11. The cylinder block as claimed in claim 9, **characterized in that** said circumferentially extending portion (72) is connected to said cylinder liner (68) at opposite sides thereof.
12. The cylinder block as claimed in claim 9, **characterized in that** said circumferentially extending portion (104) is connected to said cylinder liner (98) by a single (102) rib at a middle position between opposite sides of said circumferentially extending portion.
13. The cylinder block as claimed in claim 9, **characterized in that** said circumferentially extending portion (104) is connected to said cylinder liner by a plurality of ribs (103) each of which extends in a direction parallel to a longitudinal axis of said cylinder liner.
14. The cylinder block as claimed in claim 1, **characterized in that** an uneven portion is provided on an outer surface of said cylinder liner in a portion contacting said cylinder block body in a circumferential direction.
15. A method for manufacturing a cylinder block (10) of an internal combustion engine, comprising:

a cylinder block body (12) made of a first material; and

a cylinder liner (14) cast in said cylinder block body, said cylinder liner made of a second material different from said first material, said cylinder liner having an engaging portion (26) shaped to interfit with a mating portion of said cylinder block body, said engaging portion of said cylinder liner being outside said portion mating portion in a radial direction of said cylinder liner so as to prevent separation of said cylinder liner and said cylinder block body in a radial direction of said cylinder liner, when said

cylinder block body expands in use,

said method characterised by:

a first step of placing a core (200) in a predetermined position inside a mold (202), said core having an inner surface for forming said engaging portion (26);
 a second step of die matching a liner pattern (206) with respect to said core (200), said liner pattern having a contour substantially the same as said cylinder liner (14) other than a portion corresponding to said engaging portion (26), said liner pattern (206) comprising a combination of a plurality of pieces (210-222) so that said liner pattern is die matched by positioning each of said pieces in a predetermined position inside said core (200);
 a third step of forming an outer surface forming mold (230) corresponding to an outer surface of said cylinder liner (14) by filling a mold material in a cavity formed between said mold (202) and each of said core (200) and said liner pattern (206) and solidifying the mold material in said cavity so as to unitize the mold material and said core (200);
 a fourth step of removing said liner pattern (206) from said mold (202);
 a fifth step of placing an inner surface die (236) in a predetermined position inside said outer surface forming mold (230), said inner surface die having a contour substantially the same as a contour of an inner surface of said cylinder liner (14);
 a sixth step of forming a liner forming mold (242) by filling a mold material in said inner surface die (236) so as to form an inner surface mold having a contour substantially the same as the contour of the inner surface of said cylinder liner (14) and solidifying the mold material in said inner surface die so as to unitize said outer surface forming mold (230) and said inner surface forming mold, and
 a seventh step of casting said cylinder liner by filling molten metal in a cavity (242a) formed by said outer surface forming mold and said inner surface forming mold of said liner forming mold (242); and
 an eight step of insertion casting said cylinder block (10) with said cylinder liner (14) inserted in said cylinder block.

Patentansprüche

1. Zylinderblock eines Verbrennungsmotors mit einem aus einem ersten Material bestehenden Zylinderblockkörper und

einer in den Zylinderblockkörper eingegossenen Zylinderlaufbuchse (14, 28, 44, 38, 52, 68, 98), die aus einem zweiten Material besteht, das sich von dem ersten Material unterscheidet,

wobei die Zylinderlaufbuchse einen Eingriffabschnitt (26, 30, 40, 46, 54, 70, 100) aufweist, der so gestaltet ist, dass er zu einem Gegenabschnitt des Zylinderblockkörpers passt,

dadurch gekennzeichnet, dass sich der Eingriffabschnitt der Zylinderlaufbuchse außerhalb des Gegenabschnitts in einer radialen Richtung der Zylinderlaufbuchse befindet, um eine Trennung der Zylinderlaufbuchse und des Zylinderblockkörpers in einer radialen Richtung der Zylinderlaufbuchse zu vermeiden, wenn sich der Zylinderblockkörper bei Gebrauch ausdehnt.

2. Zylinderblock nach Anspruch 1, dadurch gekennzeichnet, dass der Eingriffabschnitt der Zylinderlaufbuchse entlang einem gesamten Umfang an einer Außenfläche der in den Zylinderblockkörper eingegossenen Zylinderlaufbuchse ausgebildet ist.
3. Zylinderblock nach Anspruch 1 oder 2, dadurch gekennzeichnet, dass der Eingriffabschnitt (26, 30, 40, 46, 54) einen Vorsprung (140, 142, 32, 34, 48, 50, 42, 56, 58) aufweist, der nach außen aus einer Außenfläche der Zylinderlaufbuchse (14, 28, 44, 38, 52) in einer radialen Richtung herausragt, wobei der Vorsprung ein Ende hat, das in einer Richtung einer Längsachse der Zylinderlaufbuchse verläuft.
4. Zylinderblock nach Anspruch 1, dadurch gekennzeichnet, dass der Eingriffabschnitt einen in der Zylinderlaufbuchse (14, 28, 44, 56) ausgebildeten hohlen Raum aufweist, der eine Öffnung in einer Außenfläche der Zylinderlaufbuchse hat, wobei, in einer radialen Richtung der Zylinderlaufbuchse gesehen, eine Fläche des hohlen Raums größer als eine Fläche der Öffnung ist.
5. Zylinderblock nach Anspruch 3, dadurch gekennzeichnet, dass der Eingriffabschnitt einen ersten Vorsprung (140, 32, 48, 56) und einen an den ersten Vorsprung angrenzenden zweiten Vorsprung (142, 34, 50, 58) aufweist, wobei der erste und der zweite Vorsprung aus einer Außenfläche der Zylinderlaufbuchse (14, 28, 44, 52) nach außen herausragen und jeweils ein Ende haben, die in entgegengesetzte Richtungen zueinander in eine Richtung einer Längsachse der Zylinderlaufbuchse verlaufen.
6. Zylinderblock nach Anspruch 3 oder 5, dadurch gekennzeichnet, dass der erste und der zweite Vorsprung (32, 34) jeweils einen unterschrittenen Abschnitt (32b, 34b) in einem Bereich haben, der, von außen in einer radialen Richtung der Zylinderlaufbuchse gesehen, mit der Außenfläche der Zylinder-

laufbuchse verbunden ist.

7. Zylinderblock nach Anspruch 3 oder 5, **dadurch gekennzeichnet, dass** ein unebener Abschnitt (60) an der Außenfläche der Zylinderlaufbuchse (52) zwischen dem ersten und zweiten Vorsprung (56, 58) entlang einer Umfangsrichtung der Zylinderlaufbuchse vorgesehen ist. 5
8. Zylinderblock nach Anspruch 3, **dadurch gekennzeichnet, dass** der Eingriffsabschnitt (46) einen ersten Vorsprung (48) und einen an den ersten Vorsprung angrenzenden zweiten Vorsprung (50) aufweist, wobei der erste und der zweite Vorsprung aus einer Außenfläche der Zylinderlaufbuchse (44) nach außen herausragen und zueinander geneigt sind. 10 15
9. Zylinderblock nach Anspruch 1 oder 2, **dadurch gekennzeichnet, dass** der Eingriffsabschnitt (70, 100) einen peripher verlaufenden Abschnitt (72, 104), der mit einer Außenfläche der Zylinderlaufbuchse (68, 98) verbunden ist, aufweist, wobei der peripher verlaufende Abschnitt in einem bestimmten Abstand (L, H) von der Außenfläche der Zylinderlaufbuchse in einer radialen Richtung der Zylinderlaufbuchse entfernt angeordnet ist und eine Vielzahl von Öffnungen (80, 108, 110) hat, die die Außen- und Innenseite des peripher verlaufenden Abschnitts verbinden. 20 25 30
10. Zylinderblock nach Anspruch 9, **dadurch gekennzeichnet, dass** der bestimmte Abstand (L, H) größer als die Breite (M, K) eines Abschnitts (12b, 12c) des Zylinderblockkörpers ist, der sich an der Außenseite des peripher verlaufenden Abschnitts befindet, wobei die Breite in einer radialen Richtung der Zylinderlaufbuchse gemessen wird. 35
11. Zylinderblock nach Anspruch 9, **dadurch gekennzeichnet, dass** der peripher verlaufende Abschnitt (72) mit der Zylinderlaufbuchse (68) an deren gegenüberliegenden Seiten verbunden ist. 40
12. Zylinderblock nach Anspruch 9, **dadurch gekennzeichnet, dass** der peripher verlaufende Abschnitt (104) mit der Zylinderlaufbuchse (98) durch eine einzelne Rippe (102) in einer mittleren Position zwischen den gegenüberliegenden Seiten des peripher verlaufenden Abschnitts verbunden ist. 45 50
13. Zylinderblock nach Anspruch 9, **dadurch gekennzeichnet, dass** der peripher verlaufende Abschnitt (104) mit der Zylinderlaufbuchse durch eine Vielzahl von Rippen (103), die jeweils parallel zur Längsachse der Zylinderlaufbuchse verlaufen, verbunden ist. 55

14. Zylinderblock nach Anspruch 1, **dadurch gekennzeichnet, dass** ein unebener Abschnitt an einer Außenfläche der Zylinderlaufbuchse in einem Abschnitt vorgesehen ist, der den Zylinderblockkörper in Umfangsrichtung berührt.

15. Verfahren zur Herstellung eines Zylinderblocks (10) eines Verbrennungsmotors mit
 einem aus einem ersten Material bestehenden Zylinderblockkörper (12) und
 einer in den Zylinderblockkörper eingegossenen Zylinderlaufbuchse (14), die aus einem zweiten Material besteht, das sich von dem ersten Material unterscheidet, wobei die Zylinderlaufbuchse einen Eingriffsabschnitt (26) hat, der so gestaltet ist, dass er zu einem Gegenabschnitt des Zylinderblockkörpers passt, und sich der Eingriffsabschnitt der Zylinderlaufbuchse außerhalb des Gegenabschnitts in einer radialen Richtung der Zylinderlaufbuchse befindet, um eine Trennung der Zylinderlaufbuchse und des Zylinderblockkörpers in einer radialen Richtung der Zylinderlaufbuchse zu vermeiden, wenn sich der Zylinderblockkörper bei Gebrauch ausdehnt,
 das folgende Schritte aufweist:

einen ersten Schritt des Anordnens eines Kerns (200) an einer bestimmten Stelle in einer Gießform (202), wobei der Kern eine Innenfläche zur Formung des Eingriffsabschnitts (26) hat;

einen zweiten Schritt des Formanpassens eines Buchsenmodells (206) an den Kern (200), wobei das Buchsenmodell eine Kontur hat, die mit Ausnahme des Abschnitts, der dem Eingriffsabschnitt (26) entspricht, weitgehend die gleiche wie die der Zylinderlaufbuchse (14) ist, wobei das Buchsenmodell (206) eine Kombination aus einer Vielzahl von Teilen (210 - 222) aufweist, sodass das Buchsenmodell durch Anordnen jedes Teils an einer bestimmten Stelle in dem Kern (200) formangepasst wird;

einen dritten Schritt des Formens einer Außenflächenformungs-Gießform (230), die einer Außenfläche des Zylinderlaufbuchse (14) entspricht, durch Einfüllen eines Formmaterials in einen zwischen der Gießform (202) und jeweils dem Kern (200) und dem Buchsenmodell (206) gebildeten Hohlraum und durch Verfestigen des Formmaterials in dem Hohlraum, um das Formmaterial und den Kern (200) zu vereinigen;

einen vierten Schritt des Abnehmens des Buchsenmodells (206) von der Gießform (202);
 einen fünften Schritt des Anordnens einer Innenflächenform (236) an einer bestimmten Stelle in der Außenflächenformungs-Gießform (230), wobei die Innenflächenform eine Kontur

hat, die weitgehend die Gleiche wie die Kontur der Innenfläche der Zylinderlaufbuchse (14) ist; einen sechsten Schritt des Formens einer Buchsenformungs-Gießform (242) durch Einfüllen eines Formmaterials in die Innenflächenform (236), um eine Innenflächen-Gießform herzustellen, die eine Kontur hat, die weitgehend die Gleiche wie die Kontur der Innenfläche der Zylinderlaufbuchse (14) ist, und durch Verfestigen des Formmaterials in der Innenflächenform, um die Außenflächenformungs-Gießform (230) und die Innenflächenformungs-Gießform zu vereinigen; einen siebenten Schritt des Gießens der Zylinderlaufbuchse durch Einfüllen von geschmolzenem Metall in einen Hohlraum (242a), der von der Außenflächenformungs-Gießform und der Innenflächenformungs-Gießform der Buchsenformungs-Gießform (242) gebildet wird; und einen achten Schritt des Eingießens des Zylinderblocks (10) mit der in den Zylinderblock eingesetzten Zylinderlaufbuchse (14).

Revendications

1. Bloc-cylindres d'un moteur à combustion interne, comprenant :
 - un corps de bloc-cylindres constitué d'un premier matériau, et
 - une chemise de cylindre (14 ; 28 ; 44 ; 38 ; 52 ; 68 ; 98) moulée dans ledit corps de bloc-cylindres, ladite chemise de cylindre étant constituée d'un second matériau différent dudit premier matériau,
 - dans lequel ladite chemise de cylindre comprend une partie de mise en prise (26 ; 30 ; 40 ; 46 ; 54 ; 70 ; 100) mise en forme pour s'adapter à une partie correspondante dudit corps de bloc-cylindres,
 - caractérisé par** ladite partie de mise en prise de ladite chemise de cylindre qui est à l'extérieur de ladite partie correspondante dans la direction radiale de ladite chemise de cylindre de façon à empêcher la séparation de ladite chemise de cylindre et dudit corps de bloc-cylindres dans la direction radiale de ladite chemise de cylindre, lorsque ledit corps de bloc-cylindres se dilate en utilisation.
2. Bloc-cylindres selon la revendication 1, dans lequel ladite partie de mise en prise de ladite chemise de cylindre est formée suivant une circonférence entière sur une surface extérieure de ladite chemise de cylindre qui est moulée dans ledit corps de bloc-cylindres.
3. Bloc-cylindres selon la revendication 2, **caractérisé en ce que** ladite partie de mise en prise (26 ; 30 ; 40 ; 46 ; 54) comprend une saillie (140 ; 142 ; 32 ; 34 ; 48 ; 50 ; 42 ; 56 ; 58) dépassant vers l'extérieur depuis une surface extérieure de ladite chemise de cylindre (14 ; 28 ; 44 ; 38 ; 52) dans la direction radiale, ladite saillie comportant une extrémité s'étendant dans la direction d'un axe longitudinal de ladite chemise de cylindre.
4. Bloc-cylindres selon la revendication 1, **caractérisé en ce que** ladite partie de mise en prise comprend un espace creux formé dans ladite chemise de cylindre (14 ; 28 ; 44 ; 56), ledit espace creux comportant une ouverture dans une surface extérieure de ladite chemise de cylindre, la superficie dudit espace creux étant supérieure à la superficie de ladite ouverture lors d'une observation dans la direction radiale de ladite chemise de cylindre.
5. Bloc-cylindres selon la revendication 3, **caractérisé en ce que** ladite partie de mise en prise comprend une première saillie (140 ; 32 ; 48 ; 56) et une seconde saillie (142 ; 34 ; 50 ; 58) adjacente à ladite première saillie, lesdites première et seconde saillies dépassant vers l'extérieur depuis une surface extérieure de ladite chemise de cylindre (14 ; 28 ; 44 ; 52), chacune desdites première et seconde saillies comportant une partie d'extrémité s'étendant dans des directions l'une vers l'autre dans la direction de l'axe longitudinal de ladite chemise de cylindre.
6. Bloc-cylindres selon la revendication 3 ou 5, **caractérisé en ce que** chacune desdites première et seconde saillies (32, 34) comporte une partie d'évidement (32b, 34b) dans une zone se raccordant à la surface extérieure de ladite chemise de cylindre lors d'une observation depuis l'extérieur dans la direction radiale de ladite chemise de cylindre.
7. Bloc-cylindres selon la revendication 3 ou 5, **caractérisé en ce qu'une** partie irrégulière (60) est prévue sur la surface extérieure de ladite chemise de cylindre (52) entre les première et seconde saillies (56, 58) le long de la direction circonférentielle de ladite chemise de cylindre.
8. Bloc-cylindres selon la revendication 3, **caractérisé en ce que** ladite partie de mise en prise (46) comprend une première saillie (48) et une seconde saillie (50) adjacente à ladite première saillie, lesdites première et seconde saillies faisant saillie vers l'extérieur depuis une surface extérieure de ladite chemise de cylindre (44), les première et seconde saillies s'inclinant l'une vers l'autre.
9. Bloc-cylindres selon la revendication 1 ou 2, **carac-**

- térisé en ce que ladite partie de mise en prise (70 ; 100) comprend une partie s'étendant sur la circonférence (72 ; 104) reliée à une surface extérieure de ladite chemise de cylindre (68 ; 98), ladite partie s'étendant sur la circonférence étant positionnée à une distance prédéterminée (L ; H) à l'écart de ladite surface extérieure de ladite chemise de cylindre dans la direction radiale de ladite chemise de cylindre, ladite partie s'étendant sur la circonférence comportant une pluralité d'ouvertures (80 ; 108 ; 100) reliant l'extérieur et l'intérieur de ladite partie s'étendant sur la circonférence. 5 10
10. Bloc-cylindres selon la revendication 9, **caractérisé en ce que** ladite distance prédéterminée (L ; H) est supérieure à la largeur (M ; K) de la partie (12b ; 12c) dudit corps de bloc-cylindres positionnée sur l'extérieur de ladite partie s'étendant sur la circonférence, ladite largeur étant mesurée dans la direction radiale de ladite chemise de cylindre. 15 20
11. Bloc-cylindres selon la revendication 9, **caractérisé en ce que** ladite partie s'étendant sur la circonférence (72) est reliée à ladite chemise de cylindre (68) au niveau de côtés opposés de celle-ci. 25
12. Bloc-cylindres selon la revendication 9, **caractérisé en ce que** ladite partie s'étendant sur la circonférence (104) est reliée à ladite chemise de cylindre (98) par une seule nervure (102) à une position intermédiaire entre les côtés opposés de ladite partie s'étendant sur la circonférence. 30
13. Bloc-cylindres selon la revendication 9, **caractérisé en ce que** ladite partie s'étendant sur la circonférence (104) est reliée à ladite chemise de cylindre par une pluralité de nervures (103), chacune d'entre elles s'étend dans une direction parallèle à l'axe longitudinal de ladite chemise de cylindre. 35 40
14. Bloc-cylindres selon la revendication 1, **caractérisé en ce qu'une** partie irrégulière est prévue sur une surface extérieure de ladite chemise de cylindre dans une partie venant en contact avec ledit corps de bloc-cylindres dans la direction circonferentielle. 45
15. Procédé de fabrication d'un bloc-cylindres (10) d'un moteur à combustion interne comprenant : 50
- un corps de bloc-cylindres (12) constitué d'un premier matériau, et
- une chemise de cylindre (14) moulée dans ledit corps de bloc-cylindres, ladite chemise de cylindre étant constituée d'un second matériau différent dudit premier matériau, ladite chemise de cylindre comportant une partie de mise en prise (26) mise en forme pour s'adapter à une 55

partie correspondante dudit corps de bloc-cylindres, ladite partie de mise en prise de ladite chemise de cylindre étant extérieure à ladite partie correspondante dans la direction radiale de ladite chemise de cylindre de façon à empêcher la séparation de ladite chemise de cylindre et dudit corps de bloc-cylindres dans la direction radiale de ladite chemise de cylindre, lorsque ledit corps de bloc-cylindres se dilate en utilisation, ledit procédé étant **caractérisé par** :

une première étape consistant à placer un noyau (200) à une position prédéterminée à l'intérieur d'un moule (202), ledit noyau comportant une surface intérieure destinée à former ladite partie de mise en prise (26),

une seconde étape consistant à adapter par rapport aux matrices un modèle de chemise (206) par rapport audit noyau (200), ledit modèle de chemise comportant un profil sensiblement identique à la chemise de cylindre (14) différente d'une partie correspondant à ladite partie de mise en prise (26), ledit modèle de chemise (206) comprenant une combinaison d'une pluralité de morceaux (210 à 222) de sorte que ledit modèle de chemise est adapté par rapport aux matrices en positionnant chacun desdits morceaux à une position prédéterminée à l'intérieur dudit noyau (200),

une troisième étape consistant à former un moule de formation de surface extérieure (230) correspondant à une surface extérieure de ladite chemise de cylindre (14) en introduisant un matériau de moule dans une cavité formée entre ledit moule (202) et chacun dudit noyau (200) et dudit modèle de chemise (206) et en solidifiant le matériau de moule dans ladite cavité de façon à rendre solidaires le matériau de moule et ledit noyau (200),

une quatrième étape consistant à enlever ledit modèle de chemise (206) dudit moule (202),

une cinquième étape consistant à placer une matrice de surface intérieure (236) à une position prédéterminée à l'intérieur dudit moule de formation de surface extérieure (230), ladite matrice de surface intérieure présentant un profil sensiblement identique au profil de la surface intérieure de ladite chemise de cylindre (14),

une sixième étape consistant à former un moule de formation de chemise (242) en introduisant un matériau de moule dans ladite matrice de surface intérieure (236) de

façon à former un moule de surface intérieure présentant un profil sensiblement identique au profil de la surface intérieure de ladite chemise de cylindre (14) et en solidifiant le matériau de moule dans ladite 5
matrice de surface intérieure de façon à rendre solidaires ledit moule de formation de surface extérieure (230) et ledit moule de formation de surface intérieure, et
une septième étape consistant à mouler la 10
dite chemise de cylindre en introduisant un métal fondu dans une cavité (242a) formée par ledit moule de formation de surface extérieure et ledit moule de formation de surface intérieure dudit moule de formation de 15
chemise (242), et
une huitième étape consistant à mouler par insertion ledit bloc-cylindres (10), ladite chemise de cylindre (14) étant insérée 20
dans ledit bloc-cylindres.

25

30

35

40

45

50

55

FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9





FIG. 10




FIG. 11




FIG. 12




FIG. 13




FIG. 14




FIG. 15




FIG. 16




FIG. 17




FIG. 18




FIG. 19




FIG. 20




FIG. 21




FIG. 22




FIG. 23




FIG. 24




FIG. 25




FIG. 26




FIG. 27




FIG. 28




FIG. 29




FIG. 30




FIG. 31




FIG. 32




FIG. 33




FIG. 34




FIG. 35




FIG. 36




FIG. 37




FIG. 38




FIG. 39




FIG. 40

